

BIODEGRADABLE MATERIAL INNOVATION FOR CONSUMER PACKAGING

Dr. Ananya Mehta

Assistant Professor

Department of Materials Science and Engineering

School of Sustainable Engineering

University of Innovation and Technology, Pune, Maharashtra, India

Abstract

Consumer packaging is expected to protect products, preserve quality, communicate information, support convenient use, and move efficiently through retail and waste-management systems. Conventional multilayer plastic structures often meet these functional requirements at low cost, but their persistence after disposal has intensified interest in material alternatives that can be sourced responsibly and managed through circular end-of-life pathways. This paper examines biodegradable material innovation for consumer packaging through a literature-informed analytical framework. It distinguishes biodegradable, compostable, bio-based, recyclable, and renewable material claims, because these terms are not interchangeable and can lead to inappropriate design or disposal decisions when used without context. The analysis evaluates major material families, including polylactic acid, polyhydroxyalkanoates, starch blends, cellulose-based systems, moulded fibre, chitosan, protein films, and hybrid bio-composites. It considers the relationship between barrier performance, mechanical strength, processing compatibility, food-contact safety, shelf-life protection, cost, consumer communication, collection infrastructure, and verified end-of-life conditions. An illustrative design-screening comparison shows that material innovation is most credible when product protection, material sourcing, conversion, disposal instructions, and local collection systems are designed together. The paper concludes that biodegradable packaging should not be positioned as a universal replacement for conventional plastics. Rather, it should be selected for defined product applications where its functional performance and end-of-life route are demonstrably aligned with the material, the market, and the available waste-management infrastructure.

Keywords: Biodegradable Packaging, Bioplastics, Consumer Packaging, Compostability, Circular Economy, Material Innovation, Sustainable Design, Life Cycle Assessment, Packaging Waste, Product Protection.

1. INTRODUCTION

Packaging is a functional system rather than a disposable afterthought. It protects products from mechanical damage, moisture, oxygen, light, odour transfer, contamination, and handling losses while also enabling transport, branding, information disclosure, and consumer convenience. Consumer markets therefore rely on a broad range of materials, including flexible films, trays, bottles, pouches, cartons, cushions, labels, coatings, and closures. However, a packaging format that performs well during production and retail can still create environmental burdens when its material composition is difficult to recover, when it contains inseparable layers, or when its disposal route is unclear. The practical challenge is not simply to replace plastic with another substrate; it is to retain essential product protection while designing a credible

route for material recovery, biodegradation, composting, reuse, or recycling.

Biodegradable material innovation has become an important part of this challenge. The term is often used broadly in commercial communication, yet the actual performance of a biodegradable material depends on its chemical structure, thickness, additives, exposure conditions, temperature, moisture, oxygen, microbial activity, and the disposal system into which it enters. A material may degrade in a controlled industrial composting environment but remain largely unchanged in a dry home-compost pile, an open landscape, a landfill, or a marine environment. Similarly, a material may be bio-based without being biodegradable, or biodegradable without being derived from renewable feedstocks. These distinctions are central to responsible packaging design because they determine

whether a stated environmental benefit can be achieved in practice.

Innovation is progressing across several material families. Polylactic acid and related polyester blends offer clarity, stiffness, and established processing routes for selected articles. Polyhydroxyalkanoates provide a biologically produced polyester platform with potential for films, coatings, and moulded items. Starch, cellulose, hemicellulose, chitosan, proteins, algae-derived polymers, agricultural residues, and moulded fibre can contribute renewable structure or barrier functionality, especially when combined in multilayer or coated designs. The most promising options are not identical across product categories. Dry foods, fresh produce, personal-care refills, takeaway articles, e-commerce protective packs, sachets, and high-fat products each impose different moisture, heat, oil, and mechanical requirements.

This study develops a structured framework for assessing biodegradable material innovation in consumer packaging. It examines material selection through five connected lenses: functional fit, material origin, manufacturing fit, consumer use, and verified end-of-life management. The framework is intended to support researchers, packaging designers, brand owners, and policy stakeholders who need to evaluate biodegradable alternatives without relying on broad environmental claims or untested assumptions.

2. LITERATURE REVIEW

Research on biodegradable packaging has evolved from early comparisons of conventional plastics and degradable polymers toward more integrated assessment of performance, safety, conversion, consumer behaviour, and end-of-life systems. Foundational reviews describe the potential of biodegradable polymers such as PLA, PHAs, starch, cellulose, and protein-based films, while also identifying limitations in moisture resistance, gas barrier properties, thermal stability, and industrial scalability. Subsequent work has examined blends, coatings,

plasticisers, fibre reinforcement, nanocomposites, and active packaging agents as ways to improve the functional performance of renewable and degradable substrates.

The literature consistently shows that product protection cannot be separated from sustainability. A packaging material that has a lower apparent material impact but causes substantial product loss may produce a less favourable whole-system outcome. This is particularly important for foods and consumer goods with high embodied resource demand. Packaging decisions should therefore be made at the level of the packaged product, not only at the level of the empty pack. Life-cycle assessment, functional-unit definition, realistic collection assumptions, transport impacts, and product-waste avoidance all influence the result of comparative environmental evaluations.

Consumer-facing claims are another major theme. Research and policy discussions warn that terms such as biodegradable, compostable, natural, and plant-based can be misunderstood when labels do not state the applicable disposal conditions. The credibility of an innovative material depends not only on its laboratory composition but also on whether the consumer can identify the correct disposal route and whether the relevant municipal or commercial system accepts the material. Clear labelling, claims substantiation, and alignment with collection infrastructure are therefore as important as polymer development.

A useful synthesis of the literature suggests that material innovation should move from a substitution model to a systems model. Instead of asking whether one polymer is intrinsically better than another, researchers should ask whether a specific material-format combination protects a particular product and can be managed responsibly in a defined market. This approach encourages application-specific testing, more transparent environmental communication, and a stronger connection between material engineering and waste-system design.

2.1 SUMMARY OF PREVIOUS STUDIES

Author(s)	Method / Technique	Major Findings	Research Gap
Song et al. (2009)	Review of biodegradable and	Explained that generic environmental claims	Needs greater application-specific comparison of

	compostable alternatives	are insufficient because materials differ in performance and end-of-life requirements.	package function and collection systems.
Siracusa et al. (2008)	Food-packaging polymer review	Identified PLA, starch, cellulose, and related materials as important biodegradable packaging platforms.	Barrier, thermal, and cost limitations remain important for demanding applications.
Peelman et al. (2013)	Application review of bioplastics	Highlighted the need to match bioplastic properties with food-packaging requirements and processing routes.	Broader consumer-product categories and disposal communication need attention.
Rhim et al. (2013)	Bio-nanocomposite review	Reported that bio-composites can improve strength and barrier performance when designed carefully.	Safety, scale-up, migration, and recyclability questions require continued evaluation.
Cheng et al. (2021)	Starch-based packaging review	Showed the versatility of starch blends and the importance of formulation and moisture management.	Commercial durability and water resistance remain key constraints.
Shaikh et al. (2021)	Overview of biodegradable food packaging	Summarised natural and synthetic biodegradable materials and their packaging applications.	Market adoption depends on economics, standards, and waste-system compatibility.
European Commission (2025)	Packaging-waste regulatory framework	Emphasised waste prevention, recyclability, and circular packaging-system design.	Material innovation must be evaluated alongside evolving regulatory requirements.

3. OBJECTIVES OF THE STUDY

The primary objective of this research is to examine biodegradable material innovation for consumer packaging through an integrated design framework that connects material performance with real-world use and end-of-life conditions. The study treats packaging as a product-protection and resource-management system, rather than evaluating biodegradability as an isolated material attribute.

3.1 PRIMARY OBJECTIVE

The primary objective of this study is to develop and apply a literature-informed framework for assessing how biodegradable materials can be selected, designed, communicated, and managed for consumer-packaging applications without compromising essential product protection or creating unsupported environmental claims.

PRIMARY OBJECTIVE POINTS

- To distinguish biodegradable, compostable, bio-based, recyclable, and renewable material characteristics in consumer-packaging design.
- To examine the functional strengths and limitations of PLA, PHAs, starch blends, cellulose systems, moulded fibre, chitosan, proteins, and hybrid bio-composites.
- To connect material selection with barrier protection, mechanical integrity, processability, safety, product shelf life, and consumer convenience.
- To evaluate the role of disposal instructions, collection systems, industrial composting access, and local waste-management capacity.
- To identify design and policy measures that can improve the credibility and

practical adoption of biodegradable packaging innovations.

3.2 SECONDARY OBJECTIVES

The secondary objectives focus on application screening, design trade-offs, consumer communication, and the institutional arrangements required to translate laboratory innovation into reliable packaging practice.

SECONDARY OBJECTIVE POINTS

- To compare product categories in which biodegradable materials may be more suitable with categories requiring high moisture, oxygen, oil, heat, or puncture resistance.
- To assess how multi-layer design, coatings, fibre reinforcement, and material blending can address performance limitations.
- To consider the effect of packaging design on product waste, transport efficiency, and retail handling.
- To examine the value of life-cycle assessment, migration testing, compostability verification, and traceable material sourcing.
- To identify communication practices that help consumers choose the correct disposal route and avoid contamination of recycling or organic-waste streams.
- To recognise the difference between illustrative design-screening values and measured product-performance data.
- To provide a framework that can be adapted for product-specific laboratory testing, consumer research, or comparative life-cycle studies.

4. RESEARCH METHODOLOGY

This paper uses a structured literature-informed analytical methodology rather than a primary survey, laboratory experiment, or market audit. The framework combines published packaging research, material-science reviews, policy guidance, and design principles to assess the conditions under which biodegradable materials may be appropriate for consumer packaging. The method is deliberately application-oriented: it does not assign a universal sustainability ranking to material families, but evaluates their fit against

a defined product, distribution context, and end-of-life route.

The analysis uses five assessment domains. The first is functional performance, including tensile behaviour, puncture resistance, stiffness, sealability, barrier performance, heat stability, visual appearance, and compatibility with the product being packed. The second is material architecture, including renewable content, additives, coatings, fibres, multilayer composition, and the possibility of unintended barriers to biodegradation or recovery. The third is manufacturing fit, covering extrusion, thermoforming, injection moulding, coating, printing, sealing, and quality control. The fourth is user and market fit, including convenience, product visibility, label clarity, consumer expectations, cost, and supply reliability. The fifth is end-of-life fit, including collection, composting or organic-waste acceptance, recycling compatibility where applicable, and evidence for the stated disposal claim.

Each proposed packaging concept is classified as low, moderate, or high readiness. Low readiness describes an option with unresolved functional, safety, processing, or end-of-life barriers. Moderate readiness describes an option that works for controlled or limited applications but requires targeted validation, a restricted product scope, or specific collection arrangements. High readiness describes an option with tested functionality, clear conversion pathways, credible claims, and an available end-of-life system. The classification is a decision-support device rather than a certification result.

The analytical comparison that follows uses illustrative scenario values to demonstrate an evaluation format. The numerical values are not presented as laboratory measurements, market-survey results, or life-cycle assessment outputs. Before an empirical paper is submitted, they should be replaced with documented package specifications, migration and shelf-life testing, local collection evidence, cost data, and a defined product and geographic market.




Figure 4.1: Illustrative Adoption Readiness Under Integrated Material Innovation

5. DATA ANALYSIS

Data analysis evaluates how an integrated biodegradable-packaging strategy can change the quality of a packaging decision across material performance, supply, consumer use, and end-of-life coordination. The comparison below contrasts a conventional material-substitution approach with an integrated innovation approach. In the first scenario, a biodegradable material is selected mainly because of a broad environmental claim, while the disposal path, product compatibility, and user information are not fully developed. In the second scenario, material choice is combined with product testing, conversion

planning, label design, collection alignment, and claim verification. The selected indicators demonstrate a possible format for a future laboratory, market, or life-cycle study.

For transparency, all values in Table 5.1 are illustrative design-screening values. They do not represent results from a field survey, a commercial pilot, a material-certification procedure, or a comparative life-cycle assessment. Their purpose is to show why a package can only be considered ready when its functional and end-of-life dimensions are assessed together.

5.1 ILLUSTRATIVE PACKAGING INNOVATION SCENARIO RESULTS

Evaluation Metric	Material-Substitution Scenario	Integrated Innovation Scenario
Product-protection alignment	57.8%	84.6%
Material-source traceability	46.2%	82.5%
Conversion and sealing reliability	61.4%	81.2%
Consumer disposal-instruction clarity	38.6%	86.1%
Collection-system compatibility	41.3%	78.4%
Claim-substantiation readiness	44.9%	83.7%
Risk of package-performance failure	29.6%	13.8%
Risk of end-of-life misdirection	46.7%	16.5%

Note: Values are illustrative scenario results used to demonstrate the evaluation format. They must be replaced with measured product, process, collection, and market evidence

before the study is presented as empirical research.

6. DISCUSSION

The analysis indicates that biodegradable material innovation should be treated as a packaging-system decision, not as a single-material decision. A formulation may have a favourable renewable-content profile but still be unsuitable for a product that requires extended moisture resistance, high-barrier protection, retort stability, aggressive chemical resistance, or a long distribution cycle. Likewise, a material that is technically compostable may not deliver a meaningful benefit when the relevant organic-waste collection route is unavailable, when the item is too small to be captured, or when consumers are asked to interpret ambiguous disposal instructions. The responsible question is therefore not whether a material is biodegradable in abstract terms; it is whether the proposed package is fit for purpose and can follow its stated recovery or degradation pathway in the market where it will be used.

Material choice should begin with the packaged product. Dry snacks, tea, coffee, confectionery, bakery products, and low-moisture personal-care goods may tolerate a wider range of cellulose, starch, PLA, or fibre-based structures than high-moisture, high-fat, carbonated, or oxygen-sensitive products. Fresh produce can benefit from breathable or compostable structures under controlled conditions, while certain products may require active or antimicrobial features that need careful food-contact assessment. Rigid trays, bottles, cups, and protective moulded parts may have different mechanical requirements from flexible sachets and films. The key design principle is to identify the product's actual failure modes first: moisture uptake, oxidation, aroma loss, crushing, leakage, temperature exposure, microbial risk, or consumer handling. Only then can an appropriate biodegradable material system be selected.

Hybrid designs can expand the application range of renewable materials, but they also create a new set of trade-offs. A starch or cellulose substrate can be reinforced with fibres, blended with biodegradable polyesters, coated with barrier layers, or combined with active agents. These interventions may improve water resistance, strength, or heat

sealing, yet they can also complicate biodegradation, increase additive scrutiny, or obscure the appropriate disposal route. Material designers must therefore understand whether each component remains compatible with the intended end-of-life claim. A coating that solves a short-term barrier problem but prevents the substrate from breaking down under the claimed composting condition can undermine the purpose of the design.

Manufacturing fit is equally important. New packaging materials must run on existing or adaptable equipment with acceptable yield, sealing consistency, print quality, and storage stability. A laboratory film may show promise but fail to scale because it warps during thermoforming, has a narrow sealing window, absorbs humidity in storage, or requires processing temperatures incompatible with the intended polymer. Innovation programmes should therefore move through staged validation: formulation screening, laboratory property testing, pilot conversion, packaged-product testing, distribution simulation, consumer-use evaluation, and end-of-life verification. Skipping these stages can create a gap between sustainability messaging and real packaging performance.

Consumer communication is a major determinant of success. Labels should tell the user what the package is made from, whether it is intended for recycling, industrial composting, home composting, or another route, and whether local acceptance is likely. A package should not imply that it will harmlessly disappear in nature. Clear icons, concise instructions, and alignment with local collection terminology can reduce confusion. When a package is accepted only in a specialised facility, that condition should be stated prominently rather than hidden in technical language. Brands should also avoid presenting biodegradability as a licence for littering, because uncontrolled disposal can still cause visual pollution, wildlife impacts, or collection-system contamination.

The broader policy and infrastructure context matters. Packaging regulations are increasingly focused on waste prevention, reuse, recycling, material safety, recycled content, and design for circularity. In this environment, biodegradable materials may be

valuable in applications where they offer a clear advantage over reusable or recyclable alternatives, particularly when contamination with food or biological residues makes conventional recovery difficult. They may be less appropriate in applications that are readily recyclable through mature systems or where reuse can be implemented effectively. A credible innovation strategy should therefore include comparative options rather than assuming that biodegradation is always the preferred endpoint.

Life-cycle thinking helps prevent narrow decision-making. Material mass alone is not an adequate indicator of environmental performance. The energy used in feedstock production, water use, agricultural land pressures, polymerisation, transport, conversion losses, product protection, collection, composting, recycling, and disposal all influence the overall result. An evidence-based study should define a functional unit such as a specified number of protected product portions delivered in acceptable condition. It should then test realistic scenarios for product loss, collection rates, and end-of-life treatment. This approach makes it possible to identify situations in which a lighter conventional package, a recyclable mono-material, a reuse system, or a biodegradable package is the better-performing choice.

The paper also highlights an equity and implementation dimension. Packaging innovation often begins in markets with sophisticated collection infrastructure, reliable composting facilities, and advanced consumer information systems. Yet many consumer goods are sold in regions where waste is collected irregularly, organic waste is not separated, and informal recyclers play a major role in material recovery. Exporting a compostable package format into such settings without supporting collection or communication can produce little real benefit. Developers should therefore assess local conditions, engage waste-management stakeholders, and avoid claims that depend on infrastructure not available to the intended users.

The primary limitation of this paper is that it provides a literature-informed framework and illustrative scenario values rather than original

laboratory measurements or market data. Future work should test defined package formats with specific products, including migration assessment, shelf-life testing, mechanical performance, process validation, consumer-disposal studies, and local end-of-life trials. Comparative studies should also report assumptions transparently so that researchers and practitioners can distinguish a promising material concept from a verified, scalable, and context-appropriate packaging solution.

7. CONCLUSION

Biodegradable Material Innovation for Consumer Packaging shows that the value of a biodegradable material depends on its fit with the whole packaging system. Material composition, functional performance, manufacturing compatibility, product protection, consumer communication, collection arrangements, and verified disposal conditions must be considered together. PLA, PHAs, starch systems, cellulose materials, moulded fibre, chitosan, protein films, and hybrid bio-composites can support meaningful innovation, but none should be treated as an automatic replacement for all conventional packaging formats.

The paper proposes a structured framework that evaluates packaging through functional fit, material architecture, manufacturing fit, user and market fit, and end-of-life fit. It emphasises that credible environmental claims require evidence about where and how the package will be collected, recycled, composted, or otherwise managed. The framework also underlines the need to protect the packaged product, because avoiding product waste is often central to the environmental performance of consumer packaging.

Future empirical research should apply this framework to product-specific packaging formats and defined geographical markets. Such research should combine material testing, conversion trials, shelf-life analysis, consumer research, waste-system evidence, and comparative life-cycle assessment. This integrated approach can help the packaging sector move from attractive but vague sustainability claims toward material innovations that are technically reliable,

clearly communicated, and environmentally credible in practice.

8. REFERENCES

1. United Nations Environment Programme. (2023). *Turning off the Tap: How the World Can End Plastic Pollution and Create a Circular Economy*. Nairobi: UNEP.
2. European Commission. (2025). *Packaging and Packaging Waste Regulation (PPWR): Packaging Waste and Circularity Requirements*. Brussels: European Commission.
3. Song, J. H., Murphy, R. J., Narayan, R., & Davies, G. B. H. (2009). Biodegradable and compostable alternatives to conventional plastics. *Philosophical Transactions of the Royal Society B*, 364(1526), 2127-2139. <https://doi.org/10.1098/rstb.2008.0289>
4. Siracusa, V., Rocculi, P., Romani, S., & Dalla Rosa, M. (2008). Biodegradable polymers for food packaging: A review. *Trends in Food Science & Technology*, 19(12), 634-643. <https://doi.org/10.1016/j.tifs.2008.07.003>
5. Peelman, N., Ragaert, P., De Meulenaer, B., Adons, D., Peeters, R., Cardon, L., Van Impe, F., & Devlieghere, F. (2013). Application of bioplastics for food packaging. *Trends in Food Science & Technology*, 32(2), 128-141. <https://doi.org/10.1016/j.tifs.2013.06.003>
6. Rhim, J.-W., Park, H.-M., & Ha, C.-S. (2013). Bio-nanocomposites for food packaging applications. *Progress in Polymer Science*, 38(10-11), 1629-1652. <https://doi.org/10.1016/j.progpolymsci.2013.05.008>
7. Cheng, H., Chen, L., McClements, D. J., Yang, T., Zhang, Z., Ren, F., Miao, M., Tian, Y., & Jin, Z. (2021). Starch-based biodegradable packaging materials: A review of their preparation, characterization and diverse applications in the food industry. *Trends in Food Science & Technology*, 114, 70-82. <https://doi.org/10.1016/j.tifs.2021.05.017>
8. Shaikh, S., Yaqoob, M., & Aggarwal, P. (2021). An overview of biodegradable packaging in food industry. *Current Research in Food Science*, 4, 503-520. <https://doi.org/10.1016/j.crfs.2021.07.005>
9. Auras, R., Harte, B., & Selke, S. (2004). An overview of polylactides as packaging materials. *Macromolecular Bioscience*, 4(9), 835-864. <https://doi.org/10.1002/mabi.200400043>
10. Iwata, T. (2015). Biodegradable and bio-based polymers: Future prospects of eco-friendly plastics. *Angewandte Chemie International Edition*, 54(11), 3210-3215. <https://doi.org/10.1002/anie.201410770>
11. Nampoothiri, K. M., Nair, N. R., & John, R. P. (2010). An overview of the recent developments in polylactide (PLA) research. *Bioresource Technology*, 101(22), 8493-8501. <https://doi.org/10.1016/j.biortech.2010.05.092>
12. Sorrentino, A., Gorrasi, G., & Vittoria, V. (2007). Potential perspectives of bio-nanocomposites for food packaging applications. *Trends in Food Science & Technology*, 18(2), 84-95. <https://doi.org/10.1016/j.tifs.2006.09.002>
13. Rastogi, V. K., & Samyn, P. (2015). Bio-based coatings for paper applications. *Coatings*, 5(4), 887-930. <https://doi.org/10.3390/coatings5040887>
14. Bordes, P., Pollet, E., & Averous, L. (2009). Nano-biocomposites: Biodegradable polyester/nanoclay systems. *Progress in Polymer Science*, 34(2), 125-155. <https://doi.org/10.1016/j.progpolymsci.2008.10.002>
15. Müller, K., Zollfrank, C., & Schmid, M. (2019). Natural polymers from biomass resources as present and future green materials. *Materials Today Sustainability*, 3-4, 100005. <https://doi.org/10.1016/j.mtsust.2019.100005>
16. Hassan, B., Chatha, S. A. S., Hussain, A. I., Zia, K. M., & Akhtar, N. (2018). Recent advances on polysaccharides, lipids and protein based edible films and coatings: A review. *International Journal of Biological Macromolecules*, 109, 1095-1107. <https://doi.org/10.1016/j.ijbiomac.2017.11.097>
17. Asgher, M., Qamar, S. A., Bilal, M., & Iqbal, H. M. N. (2020). Bio-based active food packaging materials: Sustainable alternative to conventional petrochemical-based packaging materials. *Food Research International*, 137, 109625. <https://doi.org/10.1016/j.foodres.2020.109625>

18. Wang, J., et al. (2022). Biobased materials for food packaging. *Journal of Bioresources and Bioproducts*. <https://doi.org/10.1016/j.jobab.2021.11.004>
19. Cheng, J., Sun, S., Chen, W., et al. (2024). Applications of biodegradable materials in food packaging. *Journal of King Saud University - Science*, 36, 103017.
20. Lin, J., Jaiswal, A. K., & Jaiswal, S. (2025). A critical review of consumer perception and environmental impacts of bioplastics in sustainable food packaging. *Sustainability*, 17(4), 1358. <https://doi.org/10.3390/su17041358>
21. European Commission. (2022). *Communication on an EU Policy Framework on Biobased, Biodegradable and Compostable Plastics*. Brussels: European Commission.
22. International Organization for Standardization. (2012). *ISO 18606: Packaging and the Environment - Organic Recycling*. Geneva: ISO.
23. ASTM International. (2021). *ASTM D6400: Standard Specification for Labeling of Plastics Designed to be Aerobically Composted in Municipal or Industrial Facilities*. West Conshohocken, PA: ASTM International.
24. Bhargava, N., Sharanagat, V. S., Mor, R. S., & Kumar, K. (2020). Active and intelligent biodegradable packaging films using food and food waste-derived bioactive compounds: A review. *Trends in Food Science & Technology*. <https://doi.org/10.1016/j.tifs.2020.09.015>
25. Robertson, G. L. (2016). *Food Packaging: Principles and Practice* (3rd ed.). Boca Raton, FL: CRC Press. <https://doi.org/10.1201/b21347>
26. Fonseca, A., et al. (2023). Life cycle assessment of PLA products: A systematic literature review. *Sustainability*, 15(16), 12470. <https://doi.org/10.3390/su151612470>
27. Goodrum, R., et al. (2024). Life cycle assessment of banned single-use plastic products and alternative materials. *Recycling*, 9(4), 38. <https://doi.org/10.3390/recycling9040038>
28. Thapliyal, D., et al. (2024). Current status of sustainable food packaging regulations. *Sustainability*, 16(13), 5554. <https://doi.org/10.3390/su16135554>
29. Yin, Y., et al. (2024). Transitioning of petroleum-based plastic food packaging to sustainable bio-based alternatives. *Food & Function*. <https://doi.org/10.1039/D4FB00028E>
30. Amin, U., Khan, M. K. I., Maan, A. A., Nazir, A., Riaz, S., Khan, M. U., Sultan, M., Munekata, P. E. S., & Lorenzo, J. M. (2022). Biodegradable active, intelligent, and smart packaging materials for food applications. *Food Packaging and Shelf Life*, 33, 100903. <https://doi.org/10.1016/j.fpsl.2022.100903>